

SFP15

Sil-Flex Primer



Silicone Water Repellent



Highly Breathable



Highly Polymer Technology



Excellent Adhesion

PREPARATION

All surfaces must be sound, clean, dry and free of any material which may impair adhesion. Do not apply to shiny surfaces. Scaffolding must be independently tied to allow for uninterrupted application. Any faults in the structure, particularly those which may lead to moisture penetration, must be rectified. Mask around the areas where material is to be applied. Masking tape must be removed before the material has dried out. Beads and expansion joints should be included as required by the substrate and BS standards and carried through all applied materials.

APPLICATION

To avoid dampness and discolouration, rendering should be avoided below DPC or within 150mm of ground level.

Apply with a paintbrush, lambswool roller or spray depending on the size of the substrate. eco rend SFP15 Sil-Flex Primer can be diluted with up to 2% of fresh water depending on the suction of the substrate. Stir properly before use.

Specification Clauses relating to these products can be found in NBS Section M20 & M21 rendering. BS 5262 Code of Practice for External Rendering and BS 8000-10 must be followed.

STORAGE

When stored unopened in a dry place at temperatures above +5°C, shelf life is 18 months from date of manufacture.

TOOL CLEANING

All equipment must be washed with clean water immediately after use. Waste material should not be emptied into drainage systems.

HEALTH & SAFETY INSTRUCTIONS

This product contains CMIT/MIT as a biocidal product for in-can preservation and protection of the cured product. Contains 2-Octyl-2HIsotiazol-3-One and a mixture of: 5-chloro-2- methyl-2h-isothiazol-3-one and 2-methyl-2h-Isotiazol-3-one. May produce an allergic reaction. For further information, please request the material safety data sheet for this product.

LOW VOC CONTENT: 3g/litre VOC's (Volatile Organic Compounds) contribute to atmospheric Pollution. EU limit for this product: Cat A/1 200g/l (2010). This product contains max 10g/l.

Silicone Hybrid Primer To Control Suction & Grinning

ecorend SFP15 Sil-Flex Primer is a ready to use, high-performance through coloured primer. It is designed to control the suction of the substrate and prevent any substrate grin through. For use prior to application of ecorend SF15 Sil-Flex Thin Coat Render.

Approvals and Certificates

BBA approved system – 18/5592

Technical Data

Pack Size	25kg Bucket
Application Tool	Brush, Roller or Spray
Suitable Substrate	ecorend Base Coat
Drying Time	3 to 24 hours @ +5°C to 25°C
Humidity Requirement	Less than 85% for a minimum of 24 hours
Coverage	Approx. 80m ² per 25kg bucket
Application Temperature	+5°C to 25°C for a minimum of 24 hours
Dilution Rate	Max 2%

HAZARD STATEMENT

May cause an allergic skin reaction.

PRECAUTIONARY STATEMENTS

Wear protective gloves / protective clothing / eye protection / face protection
IF ON SKIN: Wash with plenty of water. If skin irritation or rash occurs, get medical advice/attention.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

IMPORTANT INFORMATION

The weather conditions for application and drying are critical. Do not apply if any of the following conditions are likely to arise during - or in the first 24 hours following application:

- If frost is forecast, or in wet conditions
- When Relative Humidity is above 85%
- In temperatures below +5°C or above +25°C
- If the elevation is in direct sunlight
- If the substrate is hot (at or above +30°C) or below +5°C
- Substrate PH must be less than 8

Coverage rates are approx. and do not take into account wastage and uneven substrates.

The product must be protected against heavy rain, direct sun or wind in the first 24 hours after application. Sheeting the façade or the scaffold is advised to protect against this. For this particular product if these parameters are not met polymer film damage, wash off, discolouration and potential failure can occur. It is the responsibility of the application contractor to manage and record the weather conditions during application and curing of the product.

To the best of our knowledge and belief, this information is true and accurate. However, as conditions of use of the product and the expertise of any labour involved are beyond our control, the end user must satisfy themselves by prior testing that the product is suitable for their specific application if no spec has been provided for the project in hand. No responsibility can be accepted, nor any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that they have consulted our latest literature.